Resene Silvalusta

Silvalusta Resene is а solventborne black bitumen cut to brushing viscosity with the addition of a leafing grade aluminium flake.

exterior

Vehicle type Pigmentation Finish Matt Colour Silver Dry time (minimum) Recoat time (minimum) Primer required Theoretical coverage Dry film thickness Usual no. of coats Abrasion resistance Chemical resistance Heat resistance Solvent resistance Durability Thinning and clean up VOC

Physical properties

Bitumen Aluminium paste Solvent Hydrocarbon 1 hour 24 hours No 15 sq. metres per litre 23 microns at 15 sq. metres per litre 2 Poor Poor - acids and alkalis Thermoplastic Poor Good Mineral turps 509 grams per litre

Typical uses

- Bitumen roofing
- Downpipes and flashings
- Galvanised iron (new and old) •
- Roof gutters and channels •
- Water pipes

Performance

Performance

- 1. Excellent intercoat adhesion and to all surfaces.
- 2. Totally resistant to moss and mould growth.
- 3. Excellent reflective value.
- 4. Ideal on tar exteriors to reduce temperature.

Silvalusta

Surface preparation

Clean down thoroughly to remove all dirt, dust and loose material. Ensure surface is free from oil, grease, moss and mould.

If moss and mould are present, treat with Resene Moss & Mould Killer (see Data Sheet D80). Waterblasting at 21,000 kps (3000 psi) is the best surface preparation method prior to painting weathered or existing painted surfaces.

Application

Apply by brush, roller or spray. Many coats can be applied for maximum protection with no shrinking or cracking of the film.

Precautions

- 1. Resene Silvalusta develops maximum brilliance after six weeks weathering.
- 2. FLAMMABLE Keep away from heat and open flame. Keep closed when not in use.
- 3. Avoid breathing vapour use with adequate ventilation.

Please ensure the current Data Sheet is consulted prior to specification or application of Resene products. If the surface you propose to coat is not referred to by this Data Sheet, please contact Resene for clarification.

In Australia PO Box 785, Ashmore City, Queensland 4214 Call 1800 738 383, visit <u>www.resene.com.au</u> or email <u>advice@resene.com.au</u>



In New Zealand

PO Box 38242, Wellington Mail Centre, Lower Hutt 5045 Call 0800 RESENE (737 363), visit <u>www.resene.co.nz</u> or email advice@resene.co.nz

Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001. Please recycle