

net contents 1 litre

LL73701 11/23

SAFETY PRECAUTIONS

Read label before use. Keep out of reach of children. This material is quite bland; with vapour, occasional skin contact and even minor ingestion having negligible hazard. Repeated skin contact may, and any eye contact will, cause irritation. Harmful to aquatic life with long lasting effects.

PRECAUTIONS

DO NOT BREATHE DUST, MISTS, VAPOURS OR SPRAYS. DO NOT EAT, DRINK OR SMOKE WHEN USING THIS PRODUCT.

Store in original or correctly labelled container, tightly closed, in a well-ventilated area indoors, away from foodstuffs, at an ambient temperature and avoid freezing conditions. Avoid release to the environment.

FIRST AID

IF SWALLOWED: Call a POISON CENTRE, doctor or first aider if you feel unwell. IF ON SKIN (or hair): Wash with plenty of soap and water. If skin irritation occurs get medical advice or attention.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do so. Continue rinsing. If eye irritation persists get medical advice or attention. When seeking medical advice take this container with you.

Further information can be obtained from

AUST: POISONS INFORMATION CENTRE 131 126 or call Resene 1800 738 383. NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766) or call Resene 0800 737 363. For use as a filler.

For full technical instructions see Data Sheet D811.

SPILLS: Wear appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

KEEP OUT OF REACH OF CHILDREN Resene **Brushable Crack Filler**

exterior/interior



Resene Brushable Crack Filler is a convenient way not usually need priming. Prime smooth/glossy cementitious to deal with small cracks in concrete buildings, surfaces with Resene Concrete Primer (see Data Sheet D405) which may still be cyclically moving up to 25%. It to assist with topcoat adhesion. Spot prime nail heads is designed to handle cracks up to a maximum of 2mm wide

Preparation

• Cracks must be clean before application, which includes treating the moss and mould that they often harbour. Such treatment may be part of the moss and mould/waterblasting specification for the whole contract or individual to the cracks to be treated. In the latter case, wire brushing is recommended to remove dirt and loose material.

• If there is evidence of efflorescence, clean, then treat with Resene Aquapel (see Data Sheet D65) to reduce the incidence of further problems.

Primina

• Prime surfaces which are in poor condition, friable, powdery or chalky or affected by efflorescence with Resene Sureseal (see Data Sheet D42).

• If the edges of the crack are weak and crumbly, wire brush the crack edges to remove loose material, then prime with a penetrating sealer, such as Resene Sureseal.

Sound cementitious substrates, including fibre cement, do

(not galvanised) with Resene ArmourX Rust-Arrest (see Data Sheet RA30A). For galvanised nail heads use Resene ArmourX GP Metal Primer (see Data Sheet D411).

Application

• Apply multiple coats brushing across the grain until the crack is filled. Do not brush down the crack. Maintain good ventilation throughout the drying and post application curing period to ensure the paint is properly cured. This may require use of an extraction system when painting in marginal painting conditions. Do not use gas or diesel burners to heat coated area as these produce water that will inhibit drying and curing. Poor ventilation may affect appearance and performance.

• Resene Brushable Crack Filler is suitable for cracks up to 2mm. For larger cracks please ask Resene ColorShop or reseller staff for assistance.

Overcoating

As Resene Brushable Crack Filler will not leave a perfectly smooth surface it is recommended for use under textured or high build coatings.

Maintenance

(after a minimum of four weeks' drying)

See the Resene Caring for your paint finish brochure or the Resene website for full cleaning instructions.

Be PaintWise

For tips on responsible disposal of paint, cleaning equipment and minimising the impact of your decorating on the environment see the Resene website. Do not discharge any paint into the environment. Resene PaintWise (NZ) or paintback.com.au (Australia) accepts residual unwanted paint and packaging. Or contact your Local Authority for disposal information. Please recycle.







In Australia: Resene Paints (Aust) Limited 7 Production Ave, PO Box 918, Ashmore City, QLD 4214 Ph 1800 738 383 Visit resene.com.au

In New Zealand: Resene Paints Limited Vogel St, PO Box 38242, Wgtn Mail Centre, Lower Hutt 5045 Ph (04) 577 0500 Visit resene.co.nz

Ouick check

Use on: Exterior and interior cementitious surfaces. Coverage: Dependent on size of crack.

Dry time: Typically 1 hour. Drying is slowed by low temperatures and high humidity. Do not apply at temperatures below 10°C or when temperatures are liable to drop below this during the drying period. Do not apply under damp conditions.

Recoat time: 3 hours

Primer required: Dependent on surface.

Usual number of coats: Multiple until crack filled. Product will dry back and may require recoating to fill the crack

Application method: Brush. Do not roll or spray as the product needs to be worked across the crack. Clean up: Water, DO NOT THIN.

Colour: Light grev

Before use: Stir well with a wide flat stirrer.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy.

In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.

method and that the colour in this container is the same as select ised as a system for ontimal results. Substitution may cause substandard results vstem failure. For further painting advice and information, call 1800 738 383 (AUS) 0800 737 363 (NZ) or visit the Resene website