

Resene product labels are updated from time to time. This label is provided as a guide for this product and may differ from the label on the container you purchase. Please discuss your project with your local Resene ColorShop team or reseller to ensure you have the right products to give you the best quality finish for your specific project.

WARNING

KEEP OUT OF REACH OF CHILDREN

Resene

Cleancote dirt and mould resistant paint exterior/interior waterborne

LLCLNCOTE04 5/10

WARNING

Read label before use. Keep out of reach of children. This material may be harmful if swallowed, inhaled or absorbed through the skin. May cause an allergic skin reaction.

PRECAUTIONS

AVOID BREATHING FUMES/MISTS/SPRAYS/DUSTS. USE WITH ADEQUATE VENTILATION. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, either between 15°C-20°C or at a cool, constant temperature. Dispose of empty container safely. Wear protective gloves. Contaminated clothing should not be allowed out of the workplace. Consult Resene checklist on environmentally acceptable methods of cleaning equipment and disposing of unwanted paint. Do not contaminate any water supply.

FIRST AID

IF SWALLOWED: Rinse mouth. Call a POISON CENTRE or doctor/physician if you feel unwell.

IF ON SKIN (or hair): Wash with plenty of soap and water. If skin irritation or rash occurs seek medical attention. Wash contaminated clothing before re-use.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do. Continue rinsing.

IF INHALED: Remove to fresh air, IF BREATHING DIFFICULT GET MEDICAL ATTENTION IMMEDIATELY.

If exposed or concerned: Seek medical attention. When seeking medical advice take this container with you.

Further information can be obtained from
AUST: POISONS INFORMATION CENTRE 131 126
or call Resene 1800 738 383.

NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766)
or call Resene 0800 737 363.

Contains: Mixed fungicides 1.0%.

For use as a decorative/protective coating.

For full technical instructions see Data Sheet D317.

SPILLS: Wear appropriate clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

CLEANING PAINT EQUIPMENT: Brush/roll out as much paint as possible onto newspaper before washing brushes and rollers. Dispose of wash-up water onto grassy/unsealed area or into inside sink/basin, NOT into outside stormwater drain where it may harm fish in local waterways.



9 418022 026488

WHITE

Resene Cleancote is a dirt-resistant waterborne paint finish optimised for superior exterior durability and adhesion, combined with superb mould resistance. Formulated for hot climates, tropical conditions and offshore buildings exposed to heavy rainfall.

Preparation

- Ensure surfaces to be painted are in sound condition, dry, free from dirt, dust, loose material and salt.
- If mould is present, treat with Resene Moss & Mould Killer (see Data Sheet D80). Efflorescence on masonry **must be treated** (see Data Sheet D83).
- Remove accumulated windblown salt by washing with Resene Paint Prep and Housewash (see Data Sheet D812).
- Wherever oil and grease are present and when painting galvanised steel or Zinalume, ensure the surface to be painted is thoroughly cleaned using Resene Paint Prep and Housewash (see Data Sheet D812). Flush clean with water.
- Waterblasting is the best surface preparation prior to painting of weathered cementitious surfaces, galvanised steel and Zinalume.

• Disconnect downpipes until after the first heavy shower of rain before using for collection of drinking water. Ensure the run-off is diverted onto a garden or grassed area.

- **All sanding dusts may be harmful and appropriate protection must be worn. In particular dusts from old lead or chromate based paints or old building materials containing asbestos may be injurious to health if inhaled or ingested. Seek expert advice if the presence of these materials is suspected.**

- This product may be used to paint a wide variety of surfaces. If the surface you propose to paint is unsound or not referred to, try a small test area first or contact your local Resene ColorShop or Reseller for advice. Consult your Resene ColorShop or Reseller for technical advice on painting of old cementitious roof tiles, weathered galvanised steel or Zinalume and if corrosion is present.

Priming

- Sealants – special coating requirements of construction sealants and fillers should be followed.
- All surfaces (except timber) that are in poor condition or affected by efflorescence or which are friable, powdery or chalky must be primed with Resene Sureseal (see Data Sheet D42).
- Galvanised steel or Zinalume should not be allowed to weather. Apply one coat of Resene Galvo One (see Data Sheet D41) or Resene Galvo-Prime (see Data Sheet D402) as soon as possible. If the galvanised steel or Zinalume has weathered use only Resene Galvo One.
- Sound cementitious surfaces do not usually need priming. Prime smooth/glossy cementitious surfaces with Resene Concrete Primer (see Data Sheet D405) to assist with topcoat adhesion. Spot prime any nailheads with Resene Galvo-Prime.
- Repaints – spot prime all bare areas with the same primer shown for new work and proceed as for new work.

Application

- Apply two coats in the required colour allowing at least two hours between coats.

- Maintain good ventilation throughout the drying and curing period to ensure the paint is properly cured. Poor ventilation may inhibit curing and performance.

Maintenance

(after a minimum of four weeks' drying)
See the Resene Caring for your paint finish brochure or the Resene website for full cleaning instructions.

Be PaintWise

For tips on minimising the impact of your decorating on the environment see the Resene website.

Resene

the paint the professionals use

In Australia: Resene Paints (Aust) Limited
7 Production Ave, PO Box 785, Ashmore City, Queensland, 4214
Phone 1800 738 383 Fax 1800 064 960
Email advice@resene.com.au or visit www.resene.com.au

In New Zealand: Resene Paints Limited
Vogel Street, PO Box 38242, Wellington Mail Centre, Lower Hutt 5045
Phone (04) 577 0500 Fax (04) 577 0600
Email advice@resene.co.nz or visit www.resene.co.nz

Manufactured under a quality system certified as complying with ISO9001 by Telarc SA, an accredited certification body. This product complies with all the requirements of APAS Specification 02605. Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001, using vegetable-based inks.

net contents 4 litres

tinter included

Quick check

Use on: Cementitious surfaces including concrete, plaster, fibre cement, stucco, rough cast, brick and block work, galvanised steel or Zinalume.

Gloss level: Semi-gloss. Not for use on opening sashes and doors.

Coverage: 10-11 square metres per litre per coat. The spreading rate recommended for this product will achieve hiding in two coats for most colours. Increased spreading rates can be used but additional coats may be needed to achieve hiding. See the Resene website for more information.

Dry time (minimum): 45 minutes. Do not apply at temperatures below 20°C or when temperatures are liable to drop below this during the drying period. Drying is slowed by low temperatures and high humidity. Do not apply under damp conditions.

Recoat time (minimum): 2 hours.

Primer required: Dependent on surface.

Usual number of coats: Two. Bright colours may require an additional coat.

Application method: Brush, speed brush, synthetic fibre roller or spray.

Thinning and clean up: Water. May be thinned with up to 5% clean tap water.

Hot conditions: In hot conditions may be thinned with up to 5% Resene Hot Weather Additive to slow drying.

Colour range: Selected Resene Total Colour System, including BS5252, Multi-Finish, Whites & Neutrals and The Range.

Before use: Stir well with a wide flat stirrer.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy.

In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. For further painting advice and information, call 1800 738 383 (AUST), 0800 RESENE (NZ) or visit the Resene website.