

Resene product labels are updated from time to time. This label is provided as a guide for this product and may differ from the label on the container you purchase. Please discuss your project with your local Resene ColorShop team or reseller to ensure you have the right products to give you the best quality finish for your specific project.

# Resene

## Walk-on Concrete Clear

exterior protection for concrete and pavers  
waterborne

KEEP OUT OF REACH OF CHILDREN



CLEAR  
SATIN

LL1885201F 3/20

## net contents 1 litre

LL18852018 3/20

### SAFETY PRECAUTIONS

Read label before use. Keep out of reach of children. This material is quite bland; with vapour, occasional skin contact and even minor ingestion having negligible hazard. Repeated skin contact may, and any eye contact will cause irritation. Harmful to aquatic life. Harmful to the soil environment.

### PRECAUTIONS

USE WITH ADEQUATE VENTILATION. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, at an ambient temperature and avoid freezing conditions. Avoid release to the environment.

### FIRST AID

IF SWALLOWED: Rinse mouth. Call a POISON CENTRE, doctor or physician if you feel unwell.

IF ON SKIN (or hair): Rinse skin with plenty of soap and water, if skin irritation or rash occurs get medical advice or attention.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do so. Continue rinsing. If eye irritation persists get medical advice or attention.

IF INHALED: if breathing is difficult, remove to fresh air and keep at rest in a position comfortable for breathing.

When seeking medical advice take this container with you.

Further information can be obtained from  
AUST: POISONS INFORMATION CENTRE 131 126  
or call Resene 1800 738 383.

NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766) or call Resene 0800 737 363.

For use as a decorative/protective coating.

For full technical instructions see Data Sheet D511.

**SPILLS:** Wear appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

**CLEANING PAINT EQUIPMENT:** Brush/roll out as much paint as possible onto newspaper before washing brushes and rollers. Dispose of wash-up water onto grassy/unsealed area or into inside sink/basin, NOT into outside stormwater drain where it may harm fish in local waterways.

Resene Walk-on Concrete Clear is based on tough waterborne resins to give maximum abrasion resistance in a single pack satin finish on concrete surfaces subject to foot traffic.

### Preparation

- Ensure substrates to be coated are in sound condition, dry, free from dirt, dust, loose material, oil and salt.
- Remove accumulated windblown salt by washing with Resene Paint Prep and Housewash (see Data Sheet D812).
- New concrete must be allowed to cure for a minimum of 28 days before coating. Efflorescence on concrete must be treated, if the cause of efflorescence cannot be identified and corrected DO NOT apply Resene Walk-on Concrete Clear.
- Concrete should be diamond ground or acid etched (see Data Sheet D83) prior to clear coating. Acid etching can only be used in the absence of a curing membrane. Splash water onto the surface, if the concrete does not immediately absorb the water and darken then grinding is the only surface preparation option.

• Waterblasting is the best surface preparation for weathered concrete.

• If oil and grease are present ensure the surface is thoroughly cleaned using Resene Heavy Duty Paint Prep and Oil Remover (see Data Sheet D816). If mould is present, treat with Resene Moss & Mould Killer (see Data Sheet D80). Efflorescence on masonry must be treated (see Data Sheet D83).

• **All sanding dusts may be harmful and appropriate protection must be worn. In particular dusts from old lead or chromate based paints or old building materials containing asbestos may be injurious to health if inhaled or ingested. Seek expert advice if the presence of these materials is suspected.**

- Test for moisture by taping a 30cm square of clear plastic to concrete surface. If moisture appears under plastic after 48 hours leave and repeat test until plastic is clear.
- This product may be used to paint a wide variety of surfaces. If the surface you propose to paint is unsound or not referred to, try a small test area first or contact your local Resene ColorShop or reseller for advice.

### Application

- Do not shake contents, rather stir well with a wide flat stirrer.
- Apply one coat and allow at least two hours to dry. On old or weathered cementitious substrates seal with one coat of Resene Walk-on Concrete Clear thinned 10% with water and allow 24 hours before applying finish coats.
- Apply an additional two unthinned coats and allow at least 12 hours dry time before subjecting painted areas to light foot traffic. Allow 48 hours for full cure.
- Maintain good ventilation throughout the drying and curing period to ensure the paint is properly cured. Poor ventilation may inhibit curing and performance.
- Trafficable areas coated with this unmodified product will not comply with the Building Act Clause D1.3.3d. SURFACES COATED WITH RESENE WALK-ON CONCRETE CLEAR MAY BE SLIPPERY WHEN WET.

### Maintenance

(after a minimum of four weeks' drying)

- If cleaning is required, use Resene Paint Prep and Housewash correctly diluted with water and a soft broom to clean down the surface.
- Apply Resene Deep Clean (see Data Sheet D815) at the start of spring and autumn for control of algal growth.

### Be PaintWise

For tips on responsible disposal of paint, cleaning equipment and minimising the impact of your decorating on the environment see the Resene website. Do not discharge any paint into the environment. Resene PaintWise (NZ) or paintback.com.au (Australia) accepts residual unwanted paint and packaging. Or contact your Local Authority for disposal information.

## Quick check

**Use on:** Exterior domestic surfaces and light industrial surface areas.

**Gloss level:** Satin.

**Coverage:** 10 square metres per litre per coat (will vary with surface porosity).

**Dry time (minimum):** 1-2 hours. Drying is slowed by low temperatures and high humidity. Do not apply under damp conditions.

**Recoat time (minimum):** 2 hours.

**Primer required:** No.

**Usual number of coats:** Three.

**Application method:** Brush, swish mop or spray.

**Thinning:** In hot conditions may be thinned with up to 5% Resene In Weather Additive to slow drying.

**Clean up:** Water.

**Colour range:** Milky – dries clear.

**Before use:** Silicone treatments may affect adhesion and penetration. A test patch is recommended. Stir well with a wide flat stirrer.

**Enjoy the Resene Promise of quality on premium paints.** See your Resene ColorShop or the Resene website for a copy.

**In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.**

Please ensure that use of this product is compatible with the substrate and surface preparation method. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. Resene products are designed to be used as a system for optimal results. Substitution may cause substandard results or system failure. For further painting advice and information, call 1800 738 383 (AUSTRALIA), 0800 737 363 (NZ) or visit the Resene website.

# Resene

the paint the professionals use

In Australia: Resene Paints (Aust) Limited  
7 Production Ave, PO Box 924, Beenleigh, Qld 4207  
Ph 1800 738 383 Visit [www.resene.com.au](http://www.resene.com.au)

In New Zealand: Resene Paints Limited  
Vogel St, PO Box 38242, Wgtn Mail Centre, Lower Hutt 5045  
Ph (04) 577 0500 Visit [www.resene.co.nz](http://www.resene.co.nz)

Manufactured under a quality system certified as complying with ISO9001 by Telarc SA, an accredited certification body. Printed on environmentally responsible paper, which meets with the requirements of environmental management system EMAS. Printed using de-inkable toners for recycling with no solvent emissions.